# **FERROXCUBE**

# DATA SHEET

**3C98**Material specification

2013 Jun 03





# Material specification


#### **3C98 SPECIFICATIONS**

A low to medium frequency power material for use in power and general purpose transformers at frequencies up to 0.4 MHz.

|                | CONDITIONS               | VALUE     | UNIT              |
|----------------|--------------------------|-----------|-------------------|
| $\mu_i$        | 25 °C; ≤10 kHz; 0.25 mT  | 2500 ±20% |                   |
| μ <sub>a</sub> | 100 °C; 25 kHz; 200 mT   | ≈ 5500    |                   |
| В              | 25 °C; 10 kHz; 1200 A/m  | ≈ 530     | mT                |
|                | 100 °C; 10 kHz; 1200 A/m | ≈ 440     |                   |
| $P_V$          | 25 °C; 100 kHz; 200 mT   | ≈ 500     | kW/m <sup>3</sup> |
|                | 60 °C; 100 kHz; 200 mT   | ≈ 350     |                   |
|                | 100°C; 100 kHz; 200 mT   | ≈ 250     |                   |
| ρ              | DC; 25 °C                | ≈ 8       | $\Omega$ m        |
| T <sub>C</sub> |                          | ≥ 230     | °C                |
| density        |                          | ≈ 4850    | kg/m <sup>3</sup> |







2013 Jun 03 2

## Material specification





Fig.4 Amplitude permeability as a function of peak flux density.






Fig.6 Specific power loss as a function of peak flux density with frequency as a parameter.

10

10<sup>2</sup>

 $\hat{B}$  (mT)  $10^3$ 

10




Fig.7 Specific power loss for several frequency/flux density combinations as a function of temperature.

2013 Jun 03 3

### Material specification

3C98

#### **DATA SHEET STATUS DEFINITIONS**

| DATA SHEET<br>STATUS      | PRODUCT<br>STATUS | DEFINITIONS  |
|---------------------------|-------------------|--|
| Preliminary specification | Development       | This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.     |
| Product specification     | Production        | This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product. |

#### **DISCLAIMER**

**Life support applications** — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

#### PRODUCT STATUS DEFINITIONS

| STATUS    | INDICATION | DEFINITION   |
|-----------|------------|--|
| Prototype | prot       | These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change. |
| Design-in | des        | These products are recommended for new designs.  |
| Preferred |            | These products are recommended for use in current designs and are available via our sales channels.  |
| Support   | sup        | These products are <b>not</b> recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.         |

2013 Jun 03 4